



# Technical Data Sheet

## PSGBL54003 EXTREME MIRROR BLACK

**Description:** *PSGBL54003, Extreme Mirror Black* is a thermosetting powder coating based on a Polyester resin/binder system, which is designed for interior or exterior applications.

**Typical Applications:** Decorative finishes

<b>Typical Physical Properties:</b>	Film Thickness (ASTM D)	2.0 - 3.0 mil
	Gloss 60°angle (ASTM D-523-89)	99+%
	Hardness (ASTM D-3363-92A)	2H
	Flexibility (ASTM D-1737-89)	1/8 inch
	Adhesion (ASTM D-3359-95A)	5b (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	160/160 inch-lb.
	Exterior Durability	Excellent
	Salt Spray (ASTM B117)	1,000Hrs+ < 3mm
	Specific Gravity	1.33±0.03

**Application Data:** *PSGBL54003, Extreme Mirror Black* is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kV.

**Cure Schedules:** *PSGBL54003, Extreme Mirror Black* can be cured in a direct or indirect gas convection oven, an electric oven, or an Infra-red. A combination of any of these ovens is also suitable.

Standard Cure: 10 Minutes @ 400°F or 15 Minutes @ 375°F Peak Metal Temperature

**Storage:** Product should be stored at temperatures below 80<sup>o</sup>f, in a dry area away from any heat source.

**Notes:**

Please refer to the MSDS for safety information.

Any recommendations contained herein or any information given by any ALL POWDER PAINTS, LLC representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that ALL POWDER PAINTS, LLC will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.

4185 35<sup>th</sup> St. N.

Saint Petersburg

Florida 33714

Tel. (727) 321 7233

Fax. (727) 327 5333

[www.allpowderpaints.com](http://www.allpowderpaints.com) Email: [info@allpowderpaints.com](mailto:info@allpowderpaints.com)