



Technical Data Sheet

PCGRD537288T Teflon Candy Red - Specialty

Description: *PCGRD537288T, Teflon Candy Red* is a thermosetting powder coating based on a Specialty Teflon and Polyester resin/binder system, which is designed for interior or exterior applications.

Typical Applications: Decorative finishes

Typical Physical Properties:	Film Thickness (ASTM D)	2.0 - 3.0 mil
	Gloss 60°angle (ASTM D-523-89)	90+%
	Hardness (ASTM D-3363-92A)	2H
	Flexibility (ASTM D-1737-89)	1/8 inch
	Adhesion (ASTM D-3359-95A)	5b (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	200/200 inch-lb.
	Exterior Durability	Excellent
	Salt Spray (ASTM B117)	1,000Hrs+ < 3mm
	Specific Gravity	1.33±0.03

Using the ASTM D4518 test method, Teflon Slip powders have been proven to have a coefficient of friction a full 35% lower than other standard powder coatings.

Application Data: *PCGRD537288T, Teflon Candy Red* is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kV.

Cure Schedules: *PCGRD537288T, Teflon Candy Red* can be cured in a direct or indirect gas convection oven, an electric oven, or an Infra-red. A combination of any of these ovens is also suitable.

Standard Cure: 15 Minutes @ 375°F Peak Metal Temperature

Storage: Product should be stored at temperatures below 80^of, in a dry area away from any heat source.

Notes:
Please refer to the MSDS for safety information.

Any recommendations contained herein or any information given by any ALL POWDER PAINTS, LLC representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that ALL POWDER PAINTS, LLC will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.

Tel. (727) 851.9815

Fax. (727) 327 5333

www.allpowderpaints.com Email: info@allpowderpaints.com