



RAL 8025 River Texture PRGBR598478T

Description: *PRGBR598478T, RAL 8025 River Texture* is a thermosetting powder coating based on a Polyester resin/binder system, which is designed for interior or exterior applications.

Typical Applications: Decorative

Typical Physical Properties:	Film Thickness (ASTM D)	2.0 - 3.0 mil
	Gloss 60°angle (ASTM D-523-89)	90+%
	Hardness (ASTM D-3363-92A)	2H
	Flexibility (ASTM D-1737-89)	1/8 inch
	Adhesion (ASTM D-3359-95A)	5b (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	160/160 inch-lb.
	Exterior Durability	Good
	Salt Spray (ASTM B117)	1,000Hrs+ < 3mm
	Specific Gravity	1.33±0.03

Application Data: *PRGBR598478T, RAL 8025 River Texture* is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kV.

Cure Schedules: *PRGBR598478T, RAL 8025 River Texture* can be cured in a direct or indirect gas convection oven, an electric oven, or an Infra-red. A combination of any of these ovens is also suitable.

Standard Cure: 10 Minutes @ 340°F Peak Metal Temperature

Storage: Product should be stored at temperatures below 80⁰f, in a dry area away from any heat source.

Notes:

Please refer to the MSDS for safety information.

Any recommendations contained herein or any information given by any ALL POWDER PAINTS, LLC representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that ALL POWDER PAINTS, LLC will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.

4185 35th St. N.

Saint Petersburg

Florida 33714

Tel. (727) 851 9815

Fax. (727) 327 5333

www.allpowderpaints.com Email: info@allpowderpaints.com