

in square feet per pound at 100% efficiency												
Specific Gravity	Film Thickness											
	1 mils	1.5 mils	2 mils	2.5 mils	3 mils	3.5 mils	4 mils	4.5 mils	5 mils	6 mils	7 mils	8 mils
1	192.3	128.2	96.2	76.9	64.1	54.9	48.1	42.7	38.5	32.1	27.5	24
1.05	183.1	122.1	91.6	73.3	61	52.3	45.8	40.7	36.6	30.5	26.2	22.9
1.1	174.8	116.5	87.4	69.9	58.3	49.9	43.7	38.8	35	29.1	25	21.9
1.15	167.2	111.5	83.6	66.9	55.7	47.8	41.8	37.2	33.4	27.9	23.9	20.9
1.2	160.3	106.8	80.1	64.1	53.4	45.8	40.1	35.6	32.1	26.7	22.9	20
1.25	153.8	102.6	76.9	61.5	51.3	44	38.5	34.2	30.8	25.6	22	19.2
1.3	147.9	98.6	74	59.2	49.3	42.3	37	32.9	29.6	24.7	21.1	18.5
1.35	142.4	95	71.2	57	47.5	40.7	35.6	31.7	28.5	23.7	20.3	17.8
1.4	137.4	91.6	68.7	54.9	45.8	39.2	34.3	30.5	27.5	22.9	19.6	17.2
1.45	132.6	88.4	66.3	53	44.2	37.9	33.2	29.5	26.5	22.1	18.9	16.6
1.5	128.2	85.5	64.1	51.3	42.7	36.6	32.1	28.5	25.6	21.4	18.3	16
1.55	124.1	82.7	62	49.6	41.4	35.4	31	27.6	24.8	20.7	17.7	15.5
1.6	120.2	80.1	60.1	48.1	40.1	34.3	30	26.7	24	20	17.2	15
1.65	116.5	77.7	58.3	46.6	38.8	33.3	29.1	25.9	23.3	19.4	16.6	14.6
1.7	113.1	75.4	56.6	45.2	37.7	32.3	28.3	25.1	22.6	18.9	16.2	14.1
1.75	109.9	73.3	54.9	44	36.6	31.4	27.5	24.4	22	18.3	15.7	13.7
1.8	106.8	71.2	53.4	42.7	35.6	30.5	26.7	23.7	21.4	17.8	15.3	13.4
1.85	103.9	69.3	52	41.6	34.6	29.7	26	23.1	20.8	17.3	14.8	13
1.9	101.2	67.5	50.6	40.5	33.7	28.9	25.3	22.5	20.2	16.9	14.5	12.7
1.95	98.6	65.7	49.3	39.4	32.9	28.2	24.7	21.9	19.7	16.4	14.1	12.3
2	96.2	64.1	48.1	38.5	32.1	27.5	24	21.4	19.2	16	13.7	12